

1-COMPONENT, **READY MIXED**, VACUUM-PACKED JOINT FILLER **ALL WEATHER-USE** - NO EPOXY! - BASED ON RESIN



FUGE ReadyMix can be used for joints of terrace areas, garden paths & private driveway pavements for all types of natural stones and concrete tiles.

Application instructions

Dimensions of joints: Joint Width: **min. 5mm**
Joint Depth: min. 20mm

Processing temperature: min. +0 °C

In case of a reconstruction area, joint depth is created by blowing or washing out (30 mm). The area must be pre-wet thoroughly.

1. Pre-wet the surface
2. Open vacuum-sealed bag
3. Spread material on the surface
4. Sweep into the joints diagonally
5. Increase density and prolong curing process by rinsing with soft jet of water
6. Sweep off residues with a soft broom
7. Clean the surface with soft jet of water
8. Result: A clean and neat surface

CAUTION! The fundament must be water permeable. Concrete slabs are only suitable if the joints have min. joint depth 20mm and width 5mm top to bottom. No tapered joints.



*YouTube tutorial available [HTTPS://YOUTU.BE/BWAIHWUPHA](https://youtu.be/BWAIHWUPHA)

Material consumption per/m² (approx.)

Large Paving			Small Paving			Mosaic Paving			Slab		
Size cm*cm	Joint cm	kg/m ² use	Size cm*cm	Joint cm	kg/m ² use	Size cm*cm	Joint cm	kg/m ² use	Size cm*cm	Joint cm	kg/m ² use
16 x 16	1cm 2cm	6.0 11.8	10 x 10	1cm	9.1	6 x 6	1cm	14.1	30 x 30	1cm 2cm	1.5 4.0
14 x 14	1cm 2cm	6.6 12.3	10 x 8	1cm	10.1	5 x 5	1cm	16.5	40 x 40	1cm 2cm	2.5 5.0
12 x 12	1cm 2cm	7.6 15.0	8 x 8	1cm	11.0	4 x 4	1cm	20.2	50 x 50	1cm 2cm	2.0 4.0

IMPORTANT! Minimum grading curve of bedding sand is mandatory from 1,5 – 2,5 mm to secure water-permeability!
If lean mortar bed is needed, use following Concrete Receipt: Cement : Sand : Gravel = 1:5:2 Parts